

PRODUCT NAME: Vinylast Smithy Black HB Gloss

PRODUCT CODE: 29RGB05

PRODUCT DESCRIPTION:

A quick drying gloss vinyl one-coat specifically formulated for coating galvanised steel and many other types of metal. Has specialist adhesion promoters for a hard wearing film plus anticorrosive properties for protection.

AVAILABILITY

This product is available in sizes from 1ltr, 2.5ltr, 5ltr and 20ltr.

FURTHER INFORMATION

This product is specifically designed to be sprayed with a maximum thinning ratio of 20%. This product can be over coated after initial surface dry, to achieve desired film thickness

*Due to the protective nature of the coating, some chalking may occur on exposure/weathering. This is aesthetic and will not deter from the performance of the product.

VISCOSITY	SPECIFIC GRAVITY	GLOSS
6-8 Poise @ Roto 20c	1.08 – 1.14 SPL	Hi-Gloss 70+%

SURFACE PREPERATION AND APPLICATION

Ensure surface is free from rust, moisture, oil or other surface contamination. Can be degreased prior using 29PW05 and galvanised steel can be etched, if required, using 29MTW05.

APPLICATION

Product should ideally be applied by spray equipment. Can be brushed or rolled if required.

HEALTH & SAFETY

Refer to M.S.D.S. 29RGB prior to use. <https://www.fhbrundle.co.uk/files/file/sds/29RGB05N.pdf>

Provide adequate ventilation. Prolonged skin contact inhalation of vapour must be avoided. Eye contamination - Flush with eyewash or warm water for 10 mins. Clean hands after use.

Any person or company using this product without first making enquiries as to the suitability for the intended purpose does so at their own risk, and F.H. Brundle can accept no liability for the performance of the product or for any loss or damage arising out of such use.

Whilst every effort has been made to ensure the accuracy of the information supplied. F.H. Brundle cannot be held responsible for any errors or omissions. This product must only be employed for its original intended use. Any other use is wrong and potentially dangerous. Installation must be carried out in full compliance with current regulations. F.H. Brundle cannot be held liable for any damages resulting from wrongful, erroneous or negligent use.

RECOMMENDED W.F.T.

230-270 microns

RECOMMENDED D.F.T.

70-120 microns

THEORETICAL SPREADING RATE

5-7 Sq. Metres/Litre

DRYING TIME @ 20°C

Surface Dry: 1-2 hours

FLASH POINT 22-32°C

VOC: 530 g/litre

VOLUME SOLIDS

45% (-/+ 2%)

THINNERS: 29002

No. 1 Industrial Thinners

SHELF LIFE

12 Months

Southampton

Tel: 023 8070 3333

Fax: 023 8070 5555

Rainham

Tel: 01708 25 35 45

Fax: 01708 25 35 50

Ilkeston

Tel: 0115 930 2070

Fax: 0115 951 2455

Birmingham

Tel: 0121 565 8282

Fax: 0121 565 8292

Newton-Le-Willows

Tel: 01942 86 88 88

Fax: 01942 86 88 99

Glasgow

Tel: 0141 773 6699

Fax: 0141 773 6633



F.H. BRUNDLE
SERVING THE TRADE SINCE 1889

www.fhbrundle.co.uk
sales@brundle.com